

Reinforcements
Tapes/Sheets



TOPLINE – STRAP REINFORCEMENT TAPES

Article 1600

Natural & black

Polyester, very fine
Breaking load: 1190 N/25 mm
Extension at break: 23 %
Thickness: 0.30 mm



Article 1630

Natural & black

Nylon/Cotton, very strong
Breaking load: 1420 N/25 mm
Extension at break: 35 %
Thickness: 0.40 mm



Article 1680

Natural

Nylon/Cotton, very thin and strong
Breaking load: 630 N/25 mm
Extension at break: 26 %
Thickness: 0.16 mm



SEAM – RUBBING DOWN TAPES

Article 1250

Natural & black

Polyester knit
Fine and flexible
Controlled stretch



Article 1530

Natural

Cotton
Controlled stretch



Article 8219

Natural

Crepe Paper
Masking and rubbing down
Low stretch



UPPER REINFORCEMENT TAPES & SHEETS

Article 1700

Natural & black


Nylon, thin and fine
Breaking load: 338 N/25 mm
Extension at break: 35 %
Thickness: 0.14 mm



Article 3510

Natural & black

High-tenacity Nylon,
thin and strong
Breaking load: 630 N/25 mm
Extension at break: 26 %
Thickness: 0.16 mm



Article 1750

Natural & black

High-tenacity Nylon, very strong
Breaking load: 930 N/25 mm
Extension at break: 30 %
Thickness: 0.24 mm



Coating options:

1750	3510	1 x pressure sensitive = PS
1752	3512	1 x heat sensitive = HS
1753	3513	2 x heat sensitive = HS
1755	3515	2 x pressure sensitive = PS
1756	3516	1 x PS + Primer coating
1759	3519	1 x PS + 1 x HS

Also available: PU-coating, stiff finish (1750)



STAY REINFORCEMENT SHEETS & TAPES

Article 1800

Grey & black

Polypropylene non-woven



Article 1960

Natural & black


Polyester non-woven
light and soft



Article 2000

Grey

Polypropylene non-woven
Stiff, very strong, heavy weight



Coating options:

1961	1801	uncoated
1960	1800	1 x pressure sensitive
1962	1802	1 x heat-sensitive
1963	1803	2 x heat sensitive
	1805	2 x pressure sensitive

Because of their construction, the thickness of non-wovens may vary by $\pm 15\%$.



Cut Reinforcements

Topline/Strap Reinforcements

Depending on the leather you may select either a strong and flexible reinforcing tape like our article 1630 or, for finer leathers, a very thin reinforcement like article 1680 which should be used in a higher width to achieve the required strength.

Upper Reinforcements – Tapes and Sheets

Our strong high-tenacity Nylon articles 3510 and 1750 are available with many different coatings. Please select the proper coating option according to the different applications and leathers:

- one side pressure sensitive coating
- one side heat sensitive coating
- two sides heat sensitive coating
- two sides pressure sensitive coating

- one side pressure sensitive coating and primer coating on the reverse side. The primer coating is very adhesive friendly. In addition, it prevents fraying so that you obtain a very nice and clean open edge.
- one side pressure sensitive coating and heat sensitive coating on the reverse side. Same advantages as before, but the coating on the reverse side provides an even better bond with interlinings etc.
- PU-coatings, either primer or thermo coatings on both sides. Special coatings which create a very good bond in combination with PU adhesive
- pressure sensitive coating on a stiff-finished base material

Stay Reinforcements – Tapes and Sheets

Please ask for different coating options of the non-woven articles as well



Gebrüder Jaeger GmbH

Otto-Hahn-Str. 7
42369 Wuppertal
Germany
t +49 (0)202 24656-0
f +49 (0)202 24656-39
sales-germany@jaeger-ttc.com

Jaeger Italia Srl

Via Emilia Romagna n° 96/98
41049 Sassuolo (Mo)
Italia
t +39 0536 076168
f +39 0536 076167
sales-italy@jaeger-ttc.com

Jaeger Iberica S.L

Calle X S/N. Pol. Ind. El Oliveral
46190 Ribarroja de Túria, Valencia
Spanien
Tel. +34 963211082
E-Mail sales-spain@jaeger-ttc.com

Jaeger İzolasyon Bantları ve Yalıtım Elemanları Tic. Ltd. Şti.

Çınardere Mh. Gençlik Cd.
No:17/A 34896
Pendik / İstanbul, Turkey
t +90 216 598 1388
f +90 216 598 1388
sales-turkey@jaeger-ttc.com

Gebrüder Jaeger

Austria GesmbH
Gewerbestraße 300
8942 Wörschach
Austria
t +43 3682 24262
f +43 3682 28232
sales-austria@jaeger-ttc.com

Jaeger Nordic AB

Bellevuevägen 55
21619 Malmö
Sweden
t +46 40 128 707
jonas.bostrand@jaeger-nordic.se

Jaeger South Africa (Pty) Ltd

Unit 15A
Growth Point Industrial Park
1 Bell Street
Meadowdale, Eden-vale, 1614
South Africa
Tel. +27 68 569 6391
Fax + 49 202 24 656 995
sales-south-africa@jaeger-ttc.com

For your single sourcing and total quality requirements

- Super Tack Tapes/Sheets
- Functional Elastics
- Woven Reinforcements
- Local Reinforcement



Jaeger S.à.r.l.

10, rue Gutenberg
67610 La Wantzenau
France
t +33 38815 0875
f +33 38815 0895
info-france@jaeger-ttc.com

Jaeger USA, Inc.

198, Pickering Road, Rochester
New Hampshire 03867
USA
t +1 603 332 5816
f +1 603 335 3608
jus@jaeger-ttc.com

Jaeger Rus Ltd.

v. Petushkova 8
105425 Moskau
Russia
t +7 495 922 8354
sales-russia@jaeger-ttc.com

Jaeger Products PVT. LTD.

No: 60 & 61, Padavattamman
Industrial estate, Pattaravakkam
Chennai – 600098, India
t +91 44 4950 2627
baskar@jaegerindia.com

Jaeger Polska sp. z o.o.

ul. Żwirowa 1
64-920 Piła, Polen
Tel. +48 67 214 11 54
Fax +48 67 214 10 89
E-Mail info-jpl@jaeger-ttc.com